

Product

RCS 40 Rinseable Primer

Product Description

RCS 40 Rinseable Primer is a surface treatment solution that “chemically alters” the surface chemistry of EPDM membranes to dramatically improve adhesion of Lapolla Coating’s **RCS 5000 Restoration Coating System™**, 100% Acrylic Elastomeric Roof Coatings.

Recommended Uses

RCS 40 is formulated to prepare new and aged EPDM membranes for coating with the **RCS 5000 Restoration Coating System™**. The usage rate for **RCS 40 Rinseable Primer** is 500 sq.ft. per U.S. gallon. Clean spray equipment, tools and protective gear with warm soapy water.

Performance Characteristics

- Promotes adhesion of **RCS 5000 Restoration Coating System™** to both new and aged EPDM membranes.
- Environmentally safe (diluted rinse water).
- Easy to apply.
- Easy soap and water clean-up.
- Cleans and primes in one step. Eliminates the need for an interface primer.

Physical Properties

Appearance / Color:	Clear to pink liquid
Generic Type:	Anionic/nonionic surfactant mixture (proprietary), inorganic salts and water. This product contains phosphates (5.1% By weight).
VOC:	None
Flash Point:	Non-combustible
Viscosity:	Same as water
Environmental Statement:	Do not discharge undiluted RCS 40 in open bodies of water. *See rinse water notification on back page

Application

Apply **RCS 40 Rinseable Primer** directly to the EPDM membrane and allow to stand for a minimum of five (5) minutes. Remove with a power washer. Except for extremely soiled substrates, no pre-cleaning before application of **RCS 40 Rinseable Primer** is required. Spray apply with a garden-agricultural type sprayer or conventional airless spray equipment. **RCS 40** may also be applied with a mop.

RCS 40 Rinseable Primer is a high pH solution. Prolonged contact with skin will cause caustic burns. Read MSDS and wear recommended personal protective equipment. Due to its high pH, **RCS 40** is corrosive to certain substrates. Any overspray on metal, wood or plastic should be immediately power washed with clean water. Allow **RCS 40** to stand on the EPDM membrane for at least five (5) minutes. Power wash with a minimum 2500 psi to remove the **RCS 40** and all existing dirt, biological growth and other foreign debris. You will notice fine mica particles on the altered surface. This is a loosened release agent from the EPDM membrane. Complete removal of this material is also critical to achieve desired adhesion results with **RCS 5000 Restoration Coating System™**. The clean, “chemically altered” EPDM membrane should have a jet-black appearance. After five (5) minutes, it is safe to remove whether the solution is still wet or dry.

RCS 40 treated EPDM must be top coated with Lapolla Coatings’ **RCS 5000 Restoration Coating System™** 100% Acrylic Elastomeric Roof Coatings. **RCS 40** and **RCS 5000** work synergistically with each other. Satisfactory adhesion results are not achieved if EPDM is coated with similar “generic” roof coatings. **RCS 40** was developed specifically for use on EPDM rubber membranes. Use on other single ply membranes has not been fully studied and is not currently recommended.

Storage:

Store in a well-ventilated, dry area. Keep container closed when not in use. Keep out of reach from children.

Personal Protection:

Use safety glasses and chemically resistant gloves when handling materials.

Rinse Water Disposal:

This material, when fully diluted, may safely be diverted to the soil surface. Landscaping foliage should be rinsed clean of all residues to reduce risk to plant life. Keep rinse water out of open bodies of water, including ditches, streams, ponds and municipal storm sewers as it is potentially toxic to fish and aquatic life.

RESTORATION™ COATING SYSTEM

RCS™-40
Rinseable Primer

Rev. Date 1/9/12

First Aid:

INHALATION OF VAPOR OR MIST CAN CAUSE HEADACHE, NAUSEA AND IRRITATION OF THE NOSE, THROAT AND LUNGS. MAY CAUSE EYE AND SKIN IRRITATION.

Inhalation: Move person to fresh air. If breathing is difficult, give oxygen. Consult a physician.

Eye Contact: IMMEDIATELY flush eyes with plenty of water for 15 minutes. Get prompt medical attention.

Skin Contact: Remove contaminated clothing. Wash affected skin areas thoroughly with soap and water. Consult a physician if irritation persists.

Ingestion: DO NOT INDUCE VOMITING. Get medical attention immediately.

DISCLAIMER

The data presented herein is not intended for use by nonprofessional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer.

All guarantees and warranties as to products supplied by Lapolla Industries shall have only those guarantees and warranties expressed in writing by the manufacturer. The buyer's sole remedy as to any material claims will be against the applicator of the product. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. **NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS FOR USE, ARE MADE BY LAPOLLA WITH RESPECT TO OUR PRODUCTS OR INFORMATION SET FORTH HEREIN.**

To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact Lapolla Industries, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Lapolla Industries, Inc.'s quality control. We assume no responsibility for coverage, performance or injuries resulting from use.

